














Dim-Out 7000



Dim-Out 7000

Composition	DIN 60 001		Poyesther fibre, flocked
Fabric weight (g/m ²)	DIN EN 12127		340
Fabric thickness (mm)	DIN ISO 2286-3		0.45
Fabric width (cm)			235
Flame retardant			Type B (BS 5867)
Washing instructions			     Dust and vacuum as appropriate

Solar and optical coefficients (ASHRAE) All coefficients may have a tolerance of +/- 5%.


Colour	40	39	41	58	57	64	63	62
 T_v	0	0	0	0	0	0	0	0
 T_s	0	0	0	0	0	0	0	0
 R_s	64	64	64	64	64	64	64	64
 A_s	32	32	32	32	32	32	32	32

 **T_v** Visible light transmission (%)


 **T_s** Solar transmission (%)

 **R_s** Solar reflectance (%)


 **A_s** Solar absorption (%)



40




39




41




58




57



64



63



62