


















Alu Med



Alu Med

Composition	DIN 60 001		100% Polyester, aluminium backing
Fabric weight (g/m ²)	DIN EN 12127		95
Fabric thickness (mm)	DIN ISO 2286-3		0.19
Fabric qualities			stiff or soft
Fabric width (cm)			200
Louvre width (mm)			89, 127
Flame retardant			B1 (DIN 4102)
Colour fastness	DIN ISO 105-B02		6-7
Washing instructions			
Suitable for Wave®			Yes

Solar and optical coefficients (DIN EN 410) All coefficients may have a tolerance of +/- 5%.


Colour	10	20	30	40	50
	9	6	4	5	3
	53	55	54	56	53
	38	39	42	39	44
	9	8	7	7	6
	53	56	56	57	57
	38	36	37	36	37
	-	5	4	4	3
	0.42	0.41	0.41	0.41	0.41


 Visible light transmission (%)


 Visible light reflectance (%)


 Visible light absorption (%)

 UV transmission (%)

 Solar transmission (%)

 Solar reflectance (%)

 Solar absorption (%)

 Total g-value (Glass g-value: 0,72; 1,6 W/m² K) DIN EN 13363-1



10



20



30



40



50