














# Euroshade 2









# Euroshade 2

Composition	DIN 60 001		100% Polyester
Fabric weight (g/m <sup>2</sup> )	DIN EN 12127		180
Fabric thickness (mm)	DIN ISO 2286-3		0.21
Fabric width (cm)			183
Louvre width (mm)			89, 127
Flame retardant			B1 (DIN 4102), Type B (BS 5867)
Colour fastness	DIN ISO 105-B02		5-7
Washing instructions			

## Solar and optical coefficients (DIN EN 410) All coefficients may have a tolerance of +/- 5%.

Colour	10	20	30	40	50	60	70
 <b>T<sub>v</sub></b>	14	9	7	5	2	0	2
 <b>R<sub>v</sub></b>	80	81	78	69	66	56	62
 <b>A<sub>v</sub></b>	6	10	15	26	32	44	36
 <b>T<sub>s</sub></b>	25	20	19	17	19	4	24
 <b>R<sub>s</sub></b>	65	68	65	55	58	39	62
 <b>A<sub>s</sub></b>	10	12	16	28	23	57	14

-  Visible light transmission (%)
-  Visible light reflectance (%)
-  Visible light absorption (%)

-  Solar transmission (%)
-  Solar reflectance (%)
-  Solar absorption (%)



40



50



60



10



30



70



20